

| Data Sheet | | OP26908 Expanded Neoprene Sponge Rubber | |
|--------------------|----------|---|--|
| Data Sheet Type | Final | | |
| Material Reference | OP26908 | | |
| Polymer | CR | REACH | |
| Date Issued | 18/05/24 | | |

Description

An expanded Neoprene Sponge Rubber with ASTM D1056-14 Classification of 2C3 B2 M

Certified CFC & FCFC Free

| Specifications | Values | Test Methods |
|--|---------------------------------|--------------|
| Compression Deflection | 60-90 @25% Kpa 100-130 @ 50% | ASTM D1056 |
| Compression Set 25% Compression (22 Hours @ 23°C) 24 Hour Recovery | 1-3 % | ASTM D1056 |
| Compression Set 50% Compression (22 Hours @ 23°C) 24 Hour Recovery | 8-15 % | ASTM D1056 |
| Density | 150-200 Kg/m3 | ASTM D3575 |
| Elongation at Break | 150-200 % | ASTM D412 |
| Flame Resistance | Pass @ > 3mm | FMVSS302 |
| Highest Recommended Working Temperature | 80 °C | None |
| Intermittent Working Temperature | 120 °C | None |
| Lowest Recommended Working Temperature | -40 °C | None |
| Shore Hardness (Shore OO) | 50-60 ° Shore | None |
| Shrinkage | 3-7 % 22Hrs70 &Deg C | ASTM D573 |
| Tensile Strength | 680-750 Kpa | ASTM D412 |
| Water Absorption | 1-2 % Max Weight Change | ASTM D1056 |

Important Notes about this Material Data Sheet

This datasheet has been carefully compiled to advise you, our customer, in the best possible way. The information, figures, test values, and data correspond to actual engineering standards and are the result of many years of tests and trials. As individual operating conditions influence the application of each product, the information supplied in this datasheet can only be seen as a rough guideline. In every case it is the sole responsibility of the customer to evaluate his individual requirements, in particular whether the specified properties of our products are sufficient for





the intended use. This datasheet is subject to alteration without prior notice. All mentioned values contained herein are guiding values representing long-term experience averages. Please be aware that Test Results for individual Material Batches will only be provided if requested at the time of order and may be subject to additional charges and/or lead times. This Data Sheet supersedes all previous data sheets and any other data previously provided either Verbally, Electronic or Written, with reference to the above Material Grade.