

| Data Sheet         |                     | Q853 50 Shore Neoprene Rubber Sheet to EN45545-2 |       |  |
|--------------------|---------------------|--|-------|--|
| Data Sheet Type    | Final               |  |       |  |
| Material Reference | Q853 Neoprene<br>50 | POE IN THE                                       | REACH |  |
| Polymer            | CR                  |  |       |  |
| Date Issued        | 20/05/24            |  | 9     |  |

## Description

Q853 is a European Union Manufactured Self Extinguishing Neoprene Rubber Sheet that is low smoke, low toxic rubber sheet that meets Flame Resistance standard EN45545-2.

This premium grade material is European manufactured is batch tested for complete traceability and is certified Halogen and Nitrosamine Free

| Specifications                          | Values      | Test Methods |
|---|-------------|--------------|
| Compression Set                         | 15 %        | ISO 815      |
| Elongation at Break                     | 400 %       | DIN 53504    |
| Highest Recommended Working Temperature | 100 °C      | None         |
| Lowest Recommended Working Temperature  | -40 °C      | None         |
| Shore Hardness (Shore A)                | 50 ° Shore  | None         |
| Specific Gravity                        | 1.41 g/cm 3 | ISO 1183     |
| Tear Strength                           | 4.5 N/mm    | ISO 34       |
| Tensile Strength                        | 6.5 N/mm 2  | DIN 53504    |

## **Purposes**







Flame Retardent

Oil Resistance

Weather Resistance

## **Important Notes about this Material Data Sheet**

This datasheet has been carefully compiled to advise you, our customer, in the best possible way. The information, figures, test values, and data correspond to actual engineering standards and are the result of many years of tests and trials. As individual operating conditions influence the application of each product, the information supplied in this datasheet can only be seen as a rough guideline. In every case it is the sole responsibility of the customer to evaluate his individual requirements, in particular whether the specified properties of our products are sufficient for the intended use. This datasheet is subject to alteration without prior notice. All mentioned values contained herein are guiding values representing long-term experience averages. Please be aware that Test Results for individual



Material Batches will only be provided if requested at the time of order and may be subject to additional charges and/or lead times. This Data Sheet supersedes all previous data sheets and any other data previously provided either Verbally, Electronic or Written, with reference to the above Material Grade.